

High-pressure X-ray diffraction, Raman, and computational studies of MgCl2 up to 1 Mbar: Extensive pressure stability of the B-MgCl2 layered structure.

E. Stavrou, J. M. Zaug, S. Bastea, I. W. Kuo, J. Crowhurst, B. Kalkan, Z. Konopkova, M. Kunz

October 28, 2015

APS March Meeting Baltimore, MD, United States March 14, 2016 through March 18, 2016

Disclaimer

This document was prepared as an account of work sponsored by an agency of the United States government. Neither the United States government nor Lawrence Livermore National Security, LLC, nor any of their employees makes any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States government or Lawrence Livermore National Security, LLC. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States government or Lawrence Livermore National Security, LLC, and shall not be used for advertising or product endorsement purposes.

High-pressure X-ray diffraction, Raman, and computational studies of $MgCl_2$ up to 1 Mbar: Extensive pressure stability of the β - $MgCl_2$ layered structure.

Elissaios Stavrou¹, Joseph M. Zaug¹, Sorin Bastea¹, I-Feng W. Kuo¹, Jonathan C. Crowhurst¹, Bora Kalkan², Zuzana Konopkova³ and Martin Kunz²

Magnesium chloride with the rhombohedral layered $CdCl_2$ -type structure (α -MgCl₂) has been studied using x-ray diffraction and Raman spectroscopy up to 1 Mbar (at RT). The results reveal a pressure-induced second-order phase transition to a hexagonal layered CdI_2 -type structure (β -MgCl₂) at 0.7 GPa. This phase transition mainly affects the stacking sequence of the Cl anions, resulting to a shorter c-axis. An anisotropic compression along the c-axis was observed during initial compression. Above 10 GPa, the anisotropy is altered due to the repulsion of Cl anions between adjacent perpendicular to c-axis Cl-layers.

According to previous theoretical studies, a series of phase transitions towards, initially, the 3D rutile structure (with 6-fold coordinated Mg cations) at ~17 GPa and to fluorite structure (with 8-fold coordinated Mg cations) at ~70 GPa are proposed. However, according to our experimental results MgCl₂ remains in a 2D layered structure up to 1Mbar keeping the 6-fold coordination of Mg cations. This observation contradicts with the general structural behavior of highly compressed AB₂ compounds; we conducted *ab-initio* DFT theoretical calculations to elucidate the mechanisms that extend the remarkable structural stability of MgCl₂.

This work was performed under the auspices of the U. S. Department of Energy by Lawrence Livermore National Security, LLC under Contract DE-AC52-07NA27344.

¹Lawrence Livermore National Laboratory, Physical and Life Sciences Directorate, P.O. Box 808 L-350, Livermore, California 94550, USA

²Advanced Light Source, Lawrence Berkeley Laboratory, Berkeley, California 94720, United States

³ Deutsches Elektronen-Synchrotron (HASYLAB), D-22607 Hamburg, Germany